

70 GSM BLACK **CHAMMY TAPE**

TECHNICAL DATA

FABRIC

<i>Weight (GMS/M2)</i>		<i>EDANA 40.3-90</i>	<i>70</i>
<i>Thickness (mm)</i>		<i>EDANA 30.4-89</i>	<i>0.51</i>
<i>Tensile Strength</i>	<i>MD</i>		<i>125</i>
<i>N/5CM</i>	<i>CD</i>	<i>EDANA 20.2-89</i>	<i>99</i>
<i>ElongationMD</i>			<i>>80</i>
<i>(%)</i>	<i>CD</i>	<i>EDANA 20.2-89</i>	<i>>90</i>
<i>Tear Strength</i>	<i>MD</i>		<i>57</i>
<i>(N)</i>	<i>CD</i>	<i>EDANA 70.2-89</i>	<i>74</i>
<i>Water Repellency</i>			
<i>(MM/H2O)</i>		<i>EDANA 120.1-80</i>	<i>135</i>
<i>Air Permeability</i>			
<i>(MM3/MM2/MIN)</i>		<i>EDANA 140.1-81</i>	<i>140</i>
<i>Abrasion Rubs/1.5kg</i>			<i>>100</i>
<i>1 house test</i>			

NOTE

Unless otherwise indicated, the figures above are average values and should not be treated at face value for specification purposes. The company reserves the right to improve products, and any change in specification will result in a re-issue of the information sheet. Customers should satisfy themselves that the tape is suitable for their requirements whether after such modification or otherwise. Please check that you have the latest issue of the information sheet. All slitting and length tolerances are to British Standards, but other tolerances are available by request.

PRODUCT REFERENCE: 490

TECHNICAL DATA

ADHESIVE

DESCRIPTION

The adhesive is a solvent free modified acrylic based on aqueous dispersions. It has an excellent tack combined with a high adhesive strength on difficult surfaces such as foams, PE and PP films.

Product Structure	Support	No support transfer tape
	Inter liner	Release paper, Yellow, 90 g/m ²
	Adhesive Weight	50g/m ²
	Total Thickness	0.05 mm
Characteristics	Temperature Resistance	from -40°C to +90°C
	Adhesive Strength	20N/25mm
	Contact Time	1 hour

NOTE

Unless otherwise indicated, the figures above are average values and should not be treated at face value for specification purposes. The company reserves the right to improve products, and any change in specification will result in a re-issue of the information sheet. Customers should satisfy themselves that the tape is suitable for their requirements whether after such modification or otherwise. Please check that you have the latest issue of the information sheet. All slitting and length tolerances are to British Standards, but other tolerances are available by request.